

Name of Supplier: **Ruvitex UK Limited**

Origin/source of manufacturing: **001 + 002**

Product trade name: **Ruviplan F**

Description of product: **PVC-P Roofing Membrane , homogenous, non compatible with bitumen**

FPC certificate number: **1349-CPD-011**

Date of FPC certification: **06**

European standard: **EN 13956**

Type of application and roofing system: **Exposed application (mechanically fastened and for details)**

Standard dimensions: **Width: 1100mm**  
**Thickness: 1.5mm**

<u>Characteristic</u>	<u>Value or Statement</u>	<u>Test Method</u>
Visible defects	pass	EN 1850-2
Water tightness	≥ 400 kPa	EN 1928 (B)
External fire performance	B <sub>ROOF</sub> (t1)	EN 13501-5/ENV 1187
Reaction to fire	Class E	Classification after EN 13501-1
Peel resistance of joint	≥ 150 N/50mm	EN 12316-2
Shear resistance of joint	≥ 700 N/50mm	EN 12317-2
Tensile strength	≥ 16 N/50mm	EN 12311-2
Elongation at break	≥ 300%	EN 12311-2
Resistance to impact	≥ 750 mm	EN 12691 (A)
Resistance to static load	≥ 20 kg	EN 12730 (B)
Tear resistance	≥ 100 N	EN 12310-2
Dimensional stability	≤ 2.0 %	EN 1107-2
Foldability at low temperature	≤ -25 °	EN 495-5
UV exposure (1000h)	pass	EN 1297
Effects of liquid chemicals, including water (28 days/23 °C)	pass	EN 1847
Hail resistance	≥ 17 m/s	EN 13583
Water vapour properties	25.500 ± 7.500	EN 1931

Version: 05/10

